



Diametri	Limiti	UN	H	d1	P	TX
5,5	Min.	11,50	2,85	5,70	~2,20	T30
	Massimo	12,20	3,20	5,90		
6,0	Min.	14,50	3,00	5,80	~2,70	T30
	Massimo	15,00	3,40	6,00		
7,0	Min.	16,50	3,40	6,80	~3,30	T30
	Massimo	17,00	3,80	7,00		

- Acciaio temperato: **C1022**
- Durezza della cassa: **HV 560 min.**
- Durezza del nucleo: **HV 300-420**