



Diametri	Limiti	UN	D	E	P	PH
3,5	Min.	8,00	3,40	2,75	~1,27	2
	Massimo	8,40	3,60	2,85		

- Acciaio al carbonio: **C1022**
- Durezza della cassa: **HV 530 min.**
- Durezza del nucleo: **HV 320-400**